- Page 12 of the abstract as filed in the PCT international application
- 6 sheets of drawings as filed in the PCT international application

August 3, 2001
Date

Attorney for Applicant

Respectfully submitted,

Richard J. Streit Reg. 25765 c/o Ladas & Parry 224 South Michigan Avenue Chicago, Illinois 60604 (312) 427-1300

We Claim:

- A method of processing an optical device incorporating a waveguide, the method comprising the step of:
- utilizing a laser to heat and thereby ablate a 5 surface of the device so as to induce a stress in said optical device and thereby alter an optical characteristic of the waveguide, wherein the power density of the laser is selected to effect surface ablation.
 - A method as claimed in claim 1 wherein the laser comprises a carbon dioxide laser source.
 - A method as claimed in any claims wherein the method is utilized to alter the birefringent properties of the waveguide.
 - A method as claimed in claim 3 wherein the TM and TE birefringent modes are substantially aligned by the method.
 - A method as claimed in any 5. dlaims further comprising the step of masking the surface with a thermally conductive material having an aperture defined to minimise exposure of the device to the laser.
 - A method as claimed in any one of the preceding claims wherein the device comprises a sensor
 - A method as claimed in any olaims further comprising the step of:
 - depositing a material layer on the
 - surface. A method as claimed in claim 7, wherein the step of depositing the material layer comprises depositing the material layer on portions of the surface affected by the ablation.
 - A method as claimed in an glaims further comprising the step of: - mounting a further component in a groove
 - formed in the surface as a result of the ablation. 10. A method as claimed in claim 7 ep 8, wherein the material layer is provided as an electrode for

35

AMENDED SHEET **IDEA/AU**

COBCCCC. COCCLCL

10

15

20

25

30

5

10

15

20

25

30

35

X

electrically contacting the device.

11. A method as claimed in claim 9, wherein the further component comprises a modulator for modulating a characteristic of the device.

12. A method as claimed in any one of the preceding claims wherein the step of utilising the laser to heat the surface is conducted at different locations of the device so as to form an optical structure.

13. A method as claimed in claim 12, wherein the optical structure comprises a grating structure.

14. A method as claimed in claims 12 cm 13, wherein the optical structure comprises a polarization filter.

15. A method as claimed in an entire proceeding claims wherein the method is used to diminish UV induced changes present in the waveguide.

16. A method as claimed in any one of the preceding claims wherein the device comprises an optical fibre.

17. A method as claimed in any one of proceeding olaims wherein the method is utilized to mark the device by way of the ablation.

18. A method as claimed in an one of the preceding claims, wherein the laser comprises a semiconductor laser operating at a wavelength of more than about 1.8 micro metre.

metre.

19. A method as claimed in claim 18, wherein the surface of the device comprises SiO₂.

20. A method as claimed in nay one of the processing wherein the method further comprises the step of providing an absorber material to facilitate the heating of the surface of the device.

21. A device incorporating a waveguide, wherein the waveguide has been processed utilizing a laser to heat and thereby ablate a surface of the device so as to induce a stress in said device and thereby alter an optical characteristic of the waveguide, wherein the power density of the laser is selected to effect ablation.